

BELZONA 2131

FN10049

Product Specification Sheet



1. PRODUCT NAME

Belzona® 2131

(D & A Fluid Elastomer)

A casting grade elastomeric repair system for resurfacing and tooling applications.

2. MANUFACTURER

Belzona Inc.,

2000 N.W. 88th Court

Miami, Florida 33172

Belzona Polymerics Ltd.,

Claro Road, Harrogate,

HG1 4DS, England.

3. PRODUCT DESCRIPTION

A two component, fluid consistency resurfacing material designed for resurfacing/coating applications and for use as a casting material in the fabrication of components.

Applications

Surfacing pumps.

Repairing diaphragms.

Replacing drive couplings.

Casting flexible molds.

Casting shock absorbers.

Casting guide bearings.

4. TECHNICAL DATA

Base Component

Appearance Oil white viscous liquid

Density 1.06 - 1.09 g/cm³

Viscosity 22,000 - 32,000
cps at 77°F (25°C)

Solidifier Component

Appearance Thin black liquid

Odor Slightly glycolic

Density 0.99 - 1.01 g/cm³

Viscosity 200 - 400 cps
at 77°F (25°C)

• **Shelf Life:**

Separate base and solidifier components shall have a shelf life of at least 3 years when stored between 32°F (0°C) and 86°F (30°C).

• **Working Life:**

Will vary according to temperature. At 77°F (25°C) the usable life of mixed material is 10 minutes.

• **Coverage Rate:**

Applied at a thickness of 10 mil. (250 microns), each 500 gram unit will cover an area of 19.5 sq.ft. (1.81 sq.m.).

• **Volume Capacity:**

The volume capacity of mixed **Belzona® 2131** is 28.5 cu.in. (468 ccs) per 500 gram unit.

• **Cure Time:**

Will be reduced for thicker sections and extended for thinner applications. At a thickness of approximately 1/10 inch (2.5 mm), allow to solidify for the times shown in the chart below before subjecting it to the conditions indicated.

5. PHYSICAL/MECHANICAL PROPERTIES

Determined after 7 days cure at 77°F (25°C).

• **Abrasion Resistance:**

DIN

The abrasion resistance of the material when tested to DIN 53-516 will be typically 130 (relative volume loss).

Taber

The Taber abrasion resistance with 1 kg load is typically:

H18 Wheels (Wet)

at 70°F (21°C) 10 mm³

at 170°F (77°C) 192 mm³

loss per 1000 cycles

H18 Wheels (Dry)

at 70°F (21°C) 33 mm³

at 170°F (77°C) 187 mm³

loss per 1000 cycles

• **Adhesion:**

Typical adhesion values achieved when the material is used in conjunction with the designated surface conditions are:

Mild steel	ASTM D429
	180 pli (3214 kgs/m)
Copper	ASTM D429
	180 pli (3214 kgs/m)
Aluminum	ASTM D429
	80 pli (1428 kgs/m)
Concrete	ASTM D4541
	900 psi (63.3 kgs/cm ²)*
Natural rubber	ASTM D413
(Shore A 70)	10 pli (178 kgs/m)*
Polychloroprene	ASTM D413
(Shore A 80)	20 pli (357 kgs/m)*
Styrene-butadiene	ASTM D413
(Shore A 70)	20 pli (357 kgs/m)*
Nitrile	ASTM D413
(Shore A 75)	10 pli (178 kgs/m)*

* *Cohesive failure in the substrate material*

• **Chemical Resistance:**

Once fully cured, the material will demonstrate excellent resistance to the following chemicals;

carbonic acid
15% hydrochloric acid
10% hydrofluoric acid
20% sulfuric acid
stearic acid
tartaric acid
10% ammonia solution
barium hydroxide
calcium hydroxide
lime water
magnesium hydroxide
25% potassium hydroxide
25% sodium hydroxide
grease
mercury
oil/water mixture
emulsion paint
distilled water
sea water
wax emulsion
fertilizer solution
starch
silicone oil
inorganic salts

* *For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.*

CURE TIMES

TEMPERATURE

	41°F (5°C)	50°F (10°C)	59°F (15°C)	68°F (20°C)	77°F (25°C)	86°F (30°C)
Movement or use involving no loading or immersion	6 hrs	4 hrs	3 hrs	2 hrs	1½ hrs	1 hr
Full mechanical or thermal loading	3 days	2 days	2 days	1 day	1 day	1 day
Immersion in chemicals	5 days	3½ days	3 days	2½ days	2 days	1½ days

• **Compression Set:**

When tested in accordance with BS903 Part A6 typical compression set is 4.9%.

• **Electrical Properties:**

Dielectric Strength

Tested to ASTM D149 is typically 500 volts/mil (20,000 volts/mm).

Dielectric Constant

Tested to ASTM D150 is typically 7.5 at 1 MHz

Dissipation Factor

Tested to ASTM D150 is typically 0.07 at 1 MHz

Volume Resistivity

Tested to ASTM D257 is typically 1.3×10^{12} ohm cm.

Surface Resistivity

Tested to ASTM D257 is typically 1.3×10^{11} ohm.

• **Elongation:**

Tested in accordance with ASTM D412 (Die C) is typically 550%.

• **Heat Resistance:**

For many typical applications the product is suitable for operation in the temperature range -40°F to 150°F (-40°C to 65°C).

• **Leachable Chlorides:**

The leachable chloride levels of the solidified material when tested to ASTM D512C will be less than 20 ppm.

• **Radiation Resistance:**

The material, when tested to BS 4247, Part 1, 1981, "Surface materials for use in radioactive areas" has a typical Decontamination Factor (DF) of 35 and an Ease of Decontamination (ED) classification of Fair.

This test determines the ease with which a radiation contaminated surface may be rendered free from contamination.

• **Sag Resistance:**

10 mil (250 microns) maximum.

• **Shore A Hardness:**

Tested in accordance with ASTM D2240 is 85.

• **Tear Strength:**

Tested in accordance with ASTM D624 is typically 350 pli.

• **Tensile Strength:**

Tested in accordance with ASTM D412 (Die C) is typically 2000 psi (141 kgs/cm²).

6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to the Belzona Instructions For Use leaflet which is enclosed with each packaged product.

7. AVAILABILITY AND COST

Belzona® 2131 is available from a network of Belzona® Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona® Distributor in your area.

8. WARRANTY

Belzona® guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona® Instructions For Use leaflet. Belzona® further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona® has no control over the use of the product described herein, no warranty for any application can be given.

9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

10. HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

11. APPROVALS/ ACCEPTANCES

GENERAL MOTORS
FORD

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2011 Belzona International Limited. Belzona® is a registered trademark.



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000
Registered Quality Management System

