

Belzona 1521

FN10037 (HTS1)



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

METALLIC SURFACES – APPLY ONLY AFTER BLAST CLEANING

- Brush away any loose contamination and remove dirt, oil, grease etc., with **Belzona® 9111** (Cleaner/Degreaser), or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).
- Select an abrasive to give the necessary standard of cleanliness and a minimum depth of profile of 3 mils (75 microns). Use only an angular abrasive.
- Blast clean the metal surface to achieve the following standard of cleanliness:-
ISO 8501-1 SA 2½ – very thorough blast cleaning
American Standard Near White Finish SSPC SP10
Swedish Standard SA2½ SIS 05 5900
- After blasting, metal surfaces should be coated before any contamination of the surface takes place.

NOTE: SALT CONTAMINATED SURFACES

The soluble salt contamination of the prepared substrate, immediately prior to application, shall be less than 20mg/m² (2µg/cm²).

Metal surfaces that have been immersed for any periods in salt solutions e.g. sea water, should be blasted to the required standard, left for 24 hours to allow the ingrained salts to sweat to the surface, then washed prior to a further brush blast to remove these. This process may need to be repeated several times to ensure complete removal of the salts. Salt removal aids are commercially available that will assist and speed salt removal. Contact Belzona for best recommendation.

2. PIT FILLING & STRIPE COATING

All welds should be prepared to NACE SP0178 Grade C or better. Deep pitting and rough welds should be smoothed out with **Belzona® 1511** mixed, applied and overcoated in accordance with the relevant IFU. All detail areas such as welds, brackets, baffles, deflectors etc. that cannot be effectively sprayed should be stripe coated by brush with **Belzona® 1591**.

3. COMBINING THE REACTIVE COMPONENTS FOR HEATED AIRLESS SPRAY

Only commence mixing once the spray equipment has been assembled and thoroughly tested - see "Instructions for spraying Belzona solvent free coatings".

WORKING LIFE

From the commencement of mixing, **Belzona® 1521** must be used within the times shown:

Temperature	68°F (20°C)	86°F (30°C)	104°F (40°C)
Use all material within	40 mins.	25 mins.	15 mins.

4. APPLYING BELZONA® 1521

FOR BEST RESULTS

Do not apply when:-

- The substrate temperature is below 41°F (5°C), above 104°F (40°C) or the relative humidity is above 85%.
- The substrate temperature is less than 5°F (3°C) above dewpoint.
- Rain, snow, fog or mist is present.
- There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil or grease from adjacent equipment or from smoke from kerosene heaters.

4.1 EQUIPMENT REQUIRED

Belzona® 1521 must be sprayed using heated airless equipment. Either a single airless pump or plural equipment, capable of metering accurately and mixing the two components, can be used. See "Instructions for spraying Belzona solvent free coatings".

Mix ratio 9.5:1 by volume
Tip Temperature 104-122°F (40-50°C)
Tip pressure (minimum) 2500 psi (172 bars)
Tip size 17-23 thou (0.43-0.58mm)

DO NOT THIN

Cleaning solvent Belzona 9121, MEK or Acetone

4.2 COVERAGE RATES

	2	1
Recommended number of coats	2	1
Target thickness 1 st coat	18 mils (450 microns)	30 mils (750 microns)
Target thickness 2nd coat	14 mils (350 microns)	N/A
Minimum total DFT	20 mils (500 microns)	20 mils (500 microns)
Maximum total DFT	40 mils (1000 microns)	40 mils (1000 microns)
Practical coverage rate 1 st coat	21.5 sq.ft (2 m ²)/litre	12.9 sq.ft (1.2 m ²)/litre
Practical coverage rate 2 nd coat	28 sq.ft (2.6 m ²)/litre	N/A
Theoretical coverage rate to achieve minimum recommended system thickness	21.5 sq.ft (2 m ²)/litre	21.5 sq.ft (2 m ²)/litre

Actual coverage rates obtained will vary according to equipment choice, application technique, component size and application environment. Interruption to application will significantly increase wastage.

Note

Total system thickness in stripe coat or repair areas should not exceed 80 mils (2000 microns).

4.3 APPLICATION AS A 2 COAT SYSTEM.

Where it is not possible to achieve a uniform coating at the required thickness, the material should be applied as a two coat system. Apply the first coat of **Belzona® 1521** at the recommended coverage rate and allow to harden for at least 16 hours.

Before applying a second coat, wash the surface of the **Belzona® 1521** with a warm detergent solution to remove any amine bloom that has formed. Rinse with clean water and allow to completely dry. Carefully grit blast to create a frosted surface free from any gloss with a target profile of 40 microns.

Apply the second coat of **Belzona® 1521**.

4.4 APPLICATION AS A 1 COAT SYSTEM.

Where application conditions permit, **Belzona® 1521** may be applied as a single coat at the recommended coverage rate.

NOTE:

Ensure maximum thickness of 40 mils (1000 microns) is not exceeded.

4.5 INSPECTION

- Immediately after application of each unit, visually inspect for pinholes and misses. Where detected, these should be immediately brushed out.
- Once the application is complete and the coating has hardened, carry out a thorough visual inspection to confirm freedom from pinholes and misses, and to identify any possible mechanical damage.
- Spark testing can be carried out to confirm coating continuity. A DC voltage of 2,400 volts is recommended to confirm that a minimum coating thickness of 20 mil (500 microns) has been achieved.

4.6 REPAIRS

Any misses, pinholes or mechanical damage found in the coating should be repaired as follows. Wash the surface of the **Belzona® 1521** with a warm detergent solution to remove any amine bloom that has formed. Rinse with clean water and allow to completely dry. Carefully grit blast or abrade to create a frosted surface free from any gloss with a target profile of 1.5 mils (40 microns) before applying further product. **Belzona® 1591** may be used for localized repairs.

4.7 CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. MEK or Acetone. Brushes spray equipment and other application tools should be cleaned using a suitable solvent such as MEK or Acetone.

5. COMPLETION OF THE MOLECULAR REACTION

The coating should be allowed to cure as follows:

Ambient temperature	Time until inspection	Time until full service	Time until post-cure (if required)	
			Dry	Wet
41°F (5°C)	48 hrs	6 days	48 hrs	72 hrs
50°F (10°C)	24 hrs	48 hrs	24 hrs	32 hrs
68°F (20°C)	6 hrs	18 hrs	6 hrs	10 hrs
86°F (30°C)	5 hrs	14 hrs	5 hrs	8 hrs
104°F (40°C)	3 hrs	8 hrs	3 hrs	5 hrs

Post-cure will generally be unnecessary as the coating will cure sufficiently at ambient temperature with full cure achieved in service. However, post-cure may be desirable to facilitate faster cure and quicker return to service (see below).

POST-CURE

If post-cure is desirable, the coating should be heated to between 122°F (50°C) and 212°F (100°C) for a minimum of 1 hour.

The coating should be allowed to cure as detailed in the above table prior to a dry (e.g. hot air) or wet (e.g. steam and liquid media) post-cure. Wet post-cure can typically be achieved during return to service, provided that the temperature ramp rate does not exceed 54°F (30°C) per hour.

If immediate exposure to aggressive media is to occur prior to achieving a 'full service' cure, post-cure is recommended. Please contact your Belzona representative to discuss specific requirements.

Coated equipment can be transported after the material has achieved the 'inspection' level of cure.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2015 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

