Belzona 2121

(D & A HI-COAT ELASTOMER)

BELZONA®
Repair • Protect • Improve

INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

a) **SURFACE PREPARATION**
(i) Metallic Surfaces
Remove all loose surface contamination and degrease with **Belzona® 9111** (Cleaner/Degreaser) or any other effective cleaner which does not leave a residue e.g. methyl ethyl ketone (MEK).

Grit blast to a minimum 3 mil (75 microns) profile. Where blasting is not practical, thorough mechanical grinding may be considered, except for applications involving tensile loads, immersion and / or fluid flow.

(ii) Flexible Surfaces (e.g. rubbers)
NOTE: Belzona® 9111 can draw processing oils and waxes to the surface of some rubbers, particularly when new, which then impairs adhesion of **Belzona® 2121.** Test for this on a small area. If, on rubbing with a rag moistened with **Belzona® 9111,** a greasy film appears, the surface should not be degreased, but simply abraded.

Undercut fine edges with a sharp knife and scuff the surface with a rotary wire brush or suitable roughing tool.

Brush away loose contamination and degrease again with **Belzona® 9111.**

b) **CONDITIONING**
Immediately, apply a thin, even coat of **Belzona® 2911** (Elastomer QD Conditioner) or **Belzona® 2921** (Elastomer GP Conditioner) onto the surface. A brush should be used as a stipple to ensure a practical coverage rate of 13 sq.ft. (1.25 m²) per unit, on steel and most metallic substrates. On well roughened rubber substrates this could be reduced by as much as 50%.

The Belzona® Conditioner must be touch dry before overcoating with **Belzona® 2121.** This will depend on the Belzona® Conditioner selected, prevailing temperature, relative humidity and substrate. At 68°F (20°C) and 50% relative humidity, the touch dry state will be achieved after the times given when applied to a steel surface. These times may be extended when applied to rubber substrates.

Conditioner	Touch Dry	Max. Overcoating
Belzona® 2911	30 min.	4 hours
Belzona® 2921	2 hours	8 hours

Under no circumstances should application of **Belzona® 2121** take place after the maximum overcoating time.

NOTE: Belzona® 2911 has an 18 month shelf life from date of manufacture when stored at 41 - 77°F (5 - 25°C) and must be used before the stated “use-by” date.

When using **Belzona® 2121** to overcoat a surface which has been treated with a **Belzona® 1000 Series** product (except **Belzona® 1221** (Super E-Metal)), the **Belzona® 1000 Series** product must first be allowed to fully cure, the surface prepared as outlined in section 1 (a) (i), and **Belzona® 2911** or **Belzona® 2921** applied as outlined in section 1 (b).

Application of **Belzona® 2121** over **Belzona® 1221** can be carried out up to 4 hours after the application of **Belzona® 1221** without the need of any surface treatment other than removal of contamination. When overcoating **Belzona® 1221** after this time, the surface should be abraded, followed by conditioning as in Section 1(b).

WHERE BELZONA® 2121 SHOULD NOT ADHERE
Brush on **Belzona® 9411** (Release Agent) and allow to dry for 15 - 20 minutes before proceeding to step 2.

2. COMBINING THE REACTIVE COMPONENTS

Both Base and Solidifier components must remain sealed until the application stage.

a) Transfer the entire contents of both Base and Solidifier containers into the mixing bowl.

b) Immediately mix together for at least two minutes and use all material within the times shown in the table below:-

Temperature	41°F (5°C)	59°F (15°C)	77°F (25°C)	86°F (30°C)
Use all material within	25 min	20 min	10 min	6 min

VOLUME CAPACITY OF MIXED BELZONA® 2121
27.95 cu.in. (458 cm³) per 500g unit.

3. APPLYING BELZONA® 2121

FOR BEST RESULTS
Do not apply when:-

i) The temperature is below 41°F (5°C) or the relative humidity is above 90%.
ii) Rain, snow, fog or mist is present.
iii) There is moisture on the surface or is likely to be deposited by subsequent condensation.
iv) The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

a) Apply the **Belzona® 2121** to the conditioned surface with a stiff bristled brush or the plastic applicator provided, to give a coverage rate of 9.8 sq.ft. (0.91 m²) at 20 mil (500 microns) thickness.

b) Apply a second coat of **Belzona® 2121** as above following the overcoating instructions in Section 6.

NOTES:

1. DIFFERENTIATION BETWEEN LAYERS

Belzona® 2121 is available in red and black, to facilitate application and to prevent misses. In service the colour of the applied product may change.

2. CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. MEK. Brushes, injection guns and other application tools should be cleaned using a suitable solvent such as **Belzona® 9121,** MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 2121** to solidify as below before subjecting it to the conditions indicated:

	Movement or use involving no loading	Full mechanical or thermal or immersion	Immersion in chemicals loading
41°F/ 5°C	6 hours	3 days	5 days
50°F/10°C	4 hours	2 days	3½ days
59°F/15°C	3 hours	2 days	3 days
68°F/20°C	2 hours	1 day	2½ days
77°F/25°C	1½ hours	1 day	2 days
86°F/30°C	1 hour	1 day	1½ days

5. STORAGE

Store in a dry environment between 41°F (5°C) and 77°F (25°C).

Inadvertent storage of **Belzona® 2100** Base below 41°F (5°C) may result in partial solidification. If this occurs, the material can be restored to its normal form by resealing the container and warming to between 104°F (40°C) and 122°F (50°C) for 3 hours in a well ventilated, dry area.

6. OVERCOATING

Application of subsequent layers of **Belzona® 2121** can be carried out up to 3 days after the previous application without need of any surface treatment other than removal of contamination.

Overcoating of aged or weathered **Belzona® 2121** is possible at any time after initial application, provide that the surface preparation techniques for flexible surfaces described in Section 1 are employed.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2011 Belzona International Limited. Belzona® is a registered trademark.

ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612
Manufactured under an ISO 9000 Registered Quality Management System

BELZONA®
Repair • Protect • Improve

Printed in England Publication No. 45-03-11