Belzona 3912

(PSC SURFACE CONDITIONER)

BELZONA®
Repair • Protect • Improve

INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

Apply ONLY to structurally sound surfaces.

a) Remove mineral chippings of ¼ inch (6 mm) or more and sweep the area clean before proceeding to (b).

b) All surfaces should be made clean, dry and firm. Treat substrates where moss, lichens and vegetation have been removed with a fungicidal wash (e.g. Nuodex or similar) applied to the manufacturers' instructions to kill off residual spores.

2. APPLYING BELZONA® 3912

Belzona® 3912 should only be applied to porous or bituminous substrates (excluding asphalt).

FOR BEST RESULTS
Do not apply when:-
(i) There is a risk of rain, snow fog or frost.
(ii) Surface temperature is 41°F (5°C) and falling, or relative humidity rises above 80%.
(iii) A combination of high relative humidity and low temperature occurs.
(iv) Any of the above conditions is likely to occur within 45 minutes.

Brush **Belzona® 3912** well into the surface, not exceeding the recommended coverage rate. Allow the minimum overcoating times to elapse before overcoating with **Belzona® 3111.** Do not leave for more than 2 days before applying **Belzona® 3111.** Should this time be exceeded, a further application of **Belzona® 3912** must be carried out prior to application of **Belzona® 3111.**

NOTE: THINNING
Under extremely warm or windy conditions it may be necessary to thin **Belzona® 3912** by up to a maximum of 5% by volume, with clean water. Standard coverage rates apply, regardless of whether or not thinning takes place.

3. TECHNICAL DATA

MINIMUM OVERCOATING TIMES:

Temperature	10°C	20°C	30°C
Overcoat with **Belzona® 3111** after	4 hrs	2 hrs	1 hr

MAXIMUM OVERCOATING TIME: 2 days

COVERAGE RATES:

Substrate	Coverage Rate per litre	
New Asbestos Cement	86.1 sq.ft.	(8.0 m²)
Old Asbestos Cement	43.0 sq.ft.	(4.0 m²)
Wood	64.6 sq.ft.	(6.0 m²)
Smooth Felt/Bitumen	64.6 sq.ft.	(6.0 m²)
Mineral Felt/Small Chippings	38.7 sq.ft.	(3.6 m²)
Concrete/Brick	41.9 sq.ft.	(3.9 m²)
Breeze Block	21.5 sq.ft.	(2.0 m²)
De-chipped Surfaces	21.5 sq.ft.	(2.0 m²)

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Material Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2011 Belzona International Limited. Belzona® is a registered trademark.

ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Manufactured under an ISO 9000 Registered Quality Management System

BELZONA®
Repair • Protect • Improve

Printed in England Publication No. 59-03-11