

Product Data

Abrasion & Cavitation Resistant Elastomer

Belzona® 2141 (ACR-Fluid Elastomer) is an elastomeric system designed for coating applications subject to the extremely high localised pressures created by cavitation and erosion.

This versatile liquid applied material retains adhesion under long term immersion and dissipates energy created under medium to high intensity cavitation conditions.

Belzona® 2141 (ACR-Fluid Elastomer) will:

- Simplify maintenance procedures
- Extend equipment life
- Protect against erosion- corrosion

Belzona® 2141 (ACR-Fluid Elastomer) can be injected/formed or applied as either a one or two coat system by brush or applicator to most common surfaces such as metals, alloys, natural and synthetic rubbers, fibreglass and composites.

Belzona® 2141

ACR-Fluid Elastomer



Rudders

Hydroelectric Turbines



Kort Nozzles

Jet Tubes

Applications for Belzona® 2141 (ACR-Fluid Elastomer) include:

- Rudders
- Propeller shaft brackets
- Propeller bolt fairings
- Kort nozzles
- Bow thrusters
- Kaplan and Francis turbines
- Wicket gates and stay vanes
- Cooling water pump impellers
- Valves
- Shafts
- Filters
- Riser seals

www.belzona.com

Belzona® provides the solution to your repair and maintenance needs.


BELZONA®
Repair • Protect • Improve

Belzona® 2141 (ACR-Fluid Elastomer) is:

Simple

- Easily mixed and applied
- Colour differentiated formulations allow two coats to be applied at the correct thickness
- Wide overcoating window

Safe

- Cold temperature cure ensures no fire risk

Versatile

- Can be used in conjunction with different Belzona® Erosion-Corrosion coatings to allow localised protection where required
- Can be injected/formed in-situ onto pre-conditioned metal and composites
- Suitable for overcoating with anti-foulings for marine use
- Resists cavitation at ultra-high velocities up to 115 Knots / 60 ms⁻¹ with no damage (PennState Tunnel Test)

Effective

- Long term adhesion retention on immersion
- High resilience: high tear strength: elongation at break (ASTM D412) typically 530%
- Meets requirements of the ASTM D3623 (90 day immersed) cathodic disbondment test
- Independent tests show performance 297% better than stainless steel and 1,394% better than E-grade steel in the ASTM G32 cavitation erosion ultra-sonic vibration test method


Belzona® 2141

ACR-Fluid Elastomer



Pumps

For more information, please contact your local Belzona® representative:



QUALITY PRODUCTS - TECHNICAL SUPPORT

The Belzona® product range is manufactured through stringent quality and environmental control guidelines complying with the internationally recognised requirements of **ISO 9001:2008** and **ISO 14001:2004**.

Belzona® has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24 hour on-site application supervision and advice.



Belzona products are manufactured under an ISO 9000 Registered Quality Management System

