

# PRODUCT SPECIFICATION SHEET

## BELZONA 1593

FN10151



### GENERAL INFORMATION

#### Product Description:

Two component, hand or spray applied, high temperature coating, suitable for continuous immersion in aqueous/hydrocarbon systems up to 320°F/160°C.

Also suitable for steaming out up to 410°F/210°C.

Exhibits excellent corrosion resistance at elevated temperatures and is resistant to a wide range of chemicals.

#### Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- |                             |                           |                 |
|-----------------------------|---------------------------|-----------------|
| - Absorbers                 | - Evaporators             | - Scrubbers     |
| - Boiler Feed Water Systems | - Heat Exchangers         | - Separators    |
| - Condensate Tanks          | - Hot Water Vessels       | - Slug Catchers |
| - Condensers                | - LP & HP Knock-Out Drums | - Storage Tanks |
| - De-aerators               | - Pipework                |                 |

### APPLICATION INFORMATION

#### Application Methods

Brush  
Applicator  
Spray

#### Application Temperature

Application should occur in the following ambient temperature range:  
50°F/10°C to 104°F/40°C

#### Coverage Rate

**Belzona 1593** shall be applied in two coats to give a minimum thickness of 20 mils (500 microns).

At a thickness of 20 mils/500 µm, the theoretical coverage rate will be 1.10 m<sup>2</sup>/kg.

#### Cure Time

Cure times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.

#### Mixed Properties

Color: Light Green or Light Grey  
Density: 1.81 g/cm<sup>3</sup>

Gel Time (BS 5350-B5): 70-110 minutes (68°F/20°C)  
Sag Resistance (BS 5350-B9): >30 mils / >750 µm  
60° Specular Gloss (ASTM D2457): 60 - 70 Gloss Units  
VOC content (ASTM D2369 / EPA ref. 24): 0.62% / 11.14 g/L

#### Mix Ratio (base : solidifier)

11 : 1 (parts by weight)

#### Overcoat Window

Overcoat times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.  
At 68°F/20°C, the maximum overcoat time will typically be 24 hours.

#### Working Life

The working life will vary according to the temperature. At 68°F/20°C, the usable life of mixed material will typically be 45 minutes, consult the Belzona IFU for specific details.

*The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.*

# PRODUCT SPECIFICATION SHEET

## BELZONA 1593

FN10151



### ABRASION

#### Taber

Dry sliding abrasion resistance, when determined in accordance with ASTM D4060 using CS17 wheels, will typically result in:

17.4 mm<sup>3</sup> loss per 1000 cycles  
(212°F/100°C cure & 68°F/20°C test)

Wet sliding abrasion resistance, when determined in accordance with ASTM D4060 using H10 wheels, will typically result in:

1042 mm<sup>3</sup> loss per 1000 cycles  
(212°F/100°C cure & 68°F/20°C test)

### ADHESION

#### Cleavage Adhesion

The Cleavage Strength when applied to grit blasted mild steel, as determined in accordance with ASTM D1062, will typically be:

1830 pli / 320 N/mm	(68°F/20°C cure & test)
980 pli / 172 N/mm	(212°F/100°C cure & 68°F/20°C test)
770 pli / 134 N/mm	(320°F/160°C cure & 68°F/20°C test)
760 pli / 132 N/mm	(212°F/100°C cure & test)
400 pli / 70 N/mm	(320°F/160°C cure & test)

#### Pull Off Adhesion

The PosiTest Dolly Pull Off Strength on 10mm thick grit blasted mild steel, as determined in accordance with ASTM D4541 and ISO 4624, will typically be:

4350 psi / 30.0 MPa	(68°F/20°C cure)
3430 psi / 23.7 MPa	(212°F/100°C cure)
2770 psi / 19.1 MPa	(284°F/140°C cure)
2290 psi / 15.8 MPa	(320°F/160°C cure)

#### Tensile Shear Adhesion

The Tensile Shear Adhesion on grit blasted mild steel, as determined in accordance with ASTM D1002, will typically be:

2900 psi / 20.0 MPa	(68°F/20°C cure & test)
2110 psi / 14.6 MPa	(212°F/100°C cure & 68°F/20°C test)
2400 psi / 16.6 MPa	(320°F/160°C cure & 68°F/20°C test)
1530 psi / 10.6 MPa	(212°F/100°C cure & test)
1790 psi / 12.3 MPa	(320°F/160°C cure & test)

### CHEMICAL ANALYSIS

The mixed **Belzona 1593** has been independently analyzed for halogens, heavy metals, and other corrosion-causing impurities, with the following typical results:

Analyte	Total Concentration (ppm)
Fluoride	68
Chloride	300
Bromide	ND (<10)
Sulfur	57
Nitrite	ND (<7)
Nitrate	7
Zinc	5.4
Antimony, Arsenic, Bismuth, Cadmium, Lead, Tin, Silver, Mercury, Gallium and Indium	ND (<5.0)

ND : Not Detected

### CHEMICAL RESISTANCE

When tested in accordance with ISO 2812 and ISO 4628, the coating demonstrates excellent resistance to a wide range of chemicals. For full details, see the **Belzona 1593** Chemical Resistance Chart

### COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

#### Compressive Yield Strength

8280 psi / 57.1 MPa	(68°F/20°C cure & test)
11460 psi / 79.0 MPa	(212°F/100°C cure & 68°F/20°C test)
13200 psi / 91.0 MPa	(320°F/160°C cure & 68°F/20°C test)
5510 psi / 38.0 MPa	(212°F/100°C cure & test)
5010 psi / 34.6 MPa	(320°F/160°C cure & test)

#### Compressive Modulus

1.81x10 <sup>5</sup> psi / 1250 MPa	(68°F/20°C cure & test)
1.66x10 <sup>5</sup> psi / 1140 MPa	(212°F/100°C cure & 68°F/20°C test)
1.68x10 <sup>5</sup> psi / 1170 MPa	(320°F/160°C cure & 68°F/20°C test)
1.20x10 <sup>5</sup> psi / 830 MPa	(212°F/100°C cure & test)
0.99x10 <sup>5</sup> psi / 680 MPa	(320°F/160°C cure & test)

### CORROSION PROTECTION

#### Cathodic Disbondment

When tested in accordance with ASTM G42 at 194°F/90°C, the average disbondment radius will typically be: 0.209 in/5.3 mm

#### Salt Spray

When tested in accordance with ASTM B117, the coating will show no signs of failure after 1000 hours continuous exposure.

# PRODUCT SPECIFICATION SHEET

## BELZONA 1593

FN10151



### ELECTRICAL PROPERTIES

When tested in accordance with ASTM D149, method A, with voltage rise of 2kV/s, typical value will be:  
Dielectric strength 27.5 kV/mm

### ELONGATION & TENSILE PROPERTIES

When determined in accordance with ASTM D638, typical values will be:

**Tensile Strength**  
2750 psi / 19.0 MPa (68°F/20°C cure & test)  
2610 psi / 18.0 MPa (212°F/100°C cure & 68°F/20°C test)  
2570 psi / 17.7 MPa (320°F/160°C cure & 68°F/20°C test)  
2070 psi / 14.3 MPa (212°F/100°C cure & test)  
1620 psi / 11.2 MPa (320°F/160°C cure & test)

**Elongation**  
0.27 % (68°F/20°C cure & test)  
0.29 % (212°F/100°C cure & 68°F/20°C test)  
0.30 % (320°F/160°C cure & 68°F/20°C test)  
0.31 % (212°F/100°C cure & test)

**Young's Modulus**  
9.30x10<sup>5</sup> psi / 6410 MPa (68°F/20°C cure & test)  
8.68x10<sup>5</sup> psi / 5980 MPa (212°F/100°C cure & 68°F/20°C test)  
9.26x10<sup>5</sup> psi / 6380 MPa (320°F/160°C cure & 68°F/20°C test)  
6.27x10<sup>5</sup> psi / 4320 MPa (212°F/100°C cure & test)  
2.40x10<sup>5</sup> psi / 1650 MPa (320°F/160°C cure & test)

### EXPLOSIVE DECOMPRESSION

When tested in accordance with NACE TM0185 using a seawater/crude oil test fluid over-pressured with 10% carbon dioxide/90% methane, the coating exhibits no breakdown after a 21 day immersion period at 248°F/120°C and 70 bar pressure followed by rapid decompression over 15 minutes.

### FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

**Flexural Strength**  
7500 psi / 51.7 MPa (68°F/20°C cure & test)  
7810 psi / 53.8 MPa (212°F/100°C cure & 68°F/20°C test)  
6880 psi / 47.4 MPa (320°F/160°C cure & 68°F/20°C test)  
4600 psi / 31.7 MPa (212°F/100°C cure & test)  
4660 psi / 32.1 MPa (320°F/160°C cure & test)

**Flexural Modulus**  
8.99x10<sup>5</sup> psi / 6200 MPa (68°F/20°C cure & test)  
8.42x10<sup>5</sup> psi / 5810 MPa (212°F/100°C cure & 68°F/20°C test)  
9.15x10<sup>5</sup> psi / 6310 MPa (320°F/160°C cure & 68°F/20°C test)  
5.19x10<sup>5</sup> psi / 3580 MPa (212°F/100°C cure & test)  
4.31x10<sup>5</sup> psi / 2970 MPa (320°F/160°C cure & test)

### HARDNESS

The Shore D and Barcol hardness, when determined in accordance with ASTM D2240 and ASTM D2583, will typically be:

	68°F/20°C cure	212°F/100°C cure	320°F/160°C cure
<b>Shore D</b>	88	89	91
<b>Barcol</b>	87	88	90

### HEAT RESISTANCE

**Heat Distortion & Glass Transition Temperature (HDT & T<sub>g</sub>)**  
The HDT and T<sub>g</sub> when determined in accordance with ASTM D648 and ISO 11357-2 respectively, following a 7 day cure period, will typically be:

Cure temperature	HDT	T <sub>g</sub>
68°F/20°C	120°F/49°C	127°F/53°C
212°F/100°C	334°F/168°C	291°F/144°C
284°F/140°C	448°F/231°C	347°F/175°C
320°F/160°C	453°F/234°C	383°F/195°C

#### Atlas Cell Cold Wall Immersion Test

When tested in accordance with NACE TM 0174 procedure A, the coating will exhibit no blistering or rusting (ASTM D714 rating 10; ASTM D610 rating 10) after 6 months immersion in water at 320°F (160°C).

#### Electrochemical Impedance Spectroscopy (EIS)

The EIS results (log<sub>10</sub>|Z|<sub>0.1Hz</sub>) determined in accordance with ISO 16773 following Atlas cell testing at 320°F/160°C will be typically:

a) Unexposed:	11.0 Ω.cm <sup>2</sup>
b) Liquid Phase:	10.8 Ω.cm <sup>2</sup>
c) Vapor Phase:	10.5 Ω.cm <sup>2</sup>

#### Immersion Resistance

Suitable for service at temperatures up to 320°F (160°C) but refer to chemical resistance data for chemical contact limitations.

#### Steam-out Resistance

The coating will exhibit no failure after 96 hours exposure to pressurised steam at 410°F/210°C

#### Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 428°F (220°C).

# PRODUCT SPECIFICATION SHEET

## BELZONA 1593

FN10151



### IMPACT RESISTANCE

#### Izod Pendulum

Izod impact strength, when determined in accordance with ASTM D256, will typically be:

Reverse	
Notched:	4.9 KJ/m <sup>2</sup> (68°F/20°C cure & test)
	3.2 KJ/m <sup>2</sup> (212°F/100°C cure & 68°F/20°C test)
	3.0 KJ/m <sup>2</sup> (320°F/160°C cure & 68°F/20°C test)
Un-notched:	
	5.7 KJ/m <sup>2</sup> (68°F/20°C cure & test)
	5.3 KJ/m <sup>2</sup> (212°F/100°C cure & 68°F/20°C test)
	3.8 KJ/m <sup>2</sup> (320°F/160°C cure & 68°F/20°C test)

### THICK FILM CRACKING RESISTANCE

When tested in accordance with NACE TM0104 no cracking was experienced when applied at three times recommended thickness and exposed for 12 weeks in sea water at 104°F (40°C).

### THERMAL PROPERTIES

#### Thermal cycling

When tested in accordance with NACE TM0304 the coating exhibited no cracking after 252 cycles between +140°F and -22°F (+60°C and -30°C).

#### Low Temperature Thermal Shock

Coated steel panels will exhibit no blistering, cracking or delamination after multiple cycles of rapid cooling from 212°F (100°C) to -76°F (-60°C).

#### Thermal Conductivity

Thermal conductivity over a range of temperatures has been determined.

Temperature	25°C	100°C	200°C
Thermal conductivity (W/m.K)	0.6258	0.6773	0.6710

#### Specific Heat Capacity

Using DSC in accordance with ASTM E1269 the Specific heat capacity has been determined over a range of temperatures.

Temperature	25°C	100°C	200°C
-------------	------	-------	-------

Specific heat capacity (J/g.K)	1108	1299	1412
--------------------------------	------	------	------

### SHELF LIFE

Separate base and solidifier components shall have a shelf life of 3 years from date of manufacture when stored in their original unopened containers between 32°F (0°C) and 86°F (30°C).

# PRODUCT SPECIFICATION SHEET

## BELZONA 1593

FN10151



### WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

### AVAILABILITY AND COST

**Belzona 1593** is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

### MANUFACTURER

Belzona Polymerics Ltd.  
Claro Road, Harrogate,  
HG1 4DS, UK

Belzona Inc.  
2000N.W. 88<sup>th</sup> Court,  
Miami, Florida, USA, 33172

### HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

### TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2019 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are  
manufactured under an  
ISO 9001 Registered  
Quality Management System*

