

Belzona 4361

FN10152



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

APPLY ONLY TO CLEAN, FIRM, DRY AND WELL ROUGHENED SURFACES.

a) SURFACE PREPARATION

(i) Concrete Surfaces

Remove all paint, tar and other coatings, as well as any loose surface material, before application of **Belzona® 4911**. Horizontal concrete surfaces, as well as new concrete, will exhibit the phenomenon of laitance which must be removed prior to application. Allow new concrete to cure for a minimum of 28 days. Floors should have an effective vapor barrier installed.

Test for presence of moisture either

- In accordance with ASTM D4263 – plastic sheet method, or
- Measure moisture content using Electronic Moisture Meter <6% moisture (<15%WME)

If test is positive for presence of moisture, test further by either

- Measure Moisture Vapor Emission Rate in accordance with ASTM F 1869 - Anhydrous Calcium Chloride test. Acceptable if <3lbs/1000ft²/24 hours (15g/m²/24 hours), or
- Measure Relative Humidity of concrete in accordance with ASTM F2170. Acceptable if <75%

Once existing concrete surfaces have been prepared in accordance with these recommendations, proceed to Section 1 (b) - "Conditioning".

NOTE:

All porous surfaces such as concrete require to be Conditioned with **Belzona® 4911** (Magma TX Conditioner).

(ii) Areas Already Treated with **Belzona® 4111** (Magma-Quartz)

Belzona® 4361 may be applied directly to **Belzona® 4111** without conditioning so long as the application takes place within 6 hours and the **Belzona® 4111** has been kept uncontaminated by foreign matter. In this case, proceed directly to Section 2 - "Combining the Reactive Components".

Where an existing **Belzona® 4111** application has been in service for longer than 6 hours, thoroughly clean and roughen the surface and then proceed to Section 2 - "Combining the Reactive Components".

b) CONDITIONING

Add the entire contents of **Belzona® 4911** (Magma TX Conditioner) Solidifier to **Belzona® 4911** Base and stir thoroughly until completely mixed. Immediately brush the Conditioner onto the surface to be treated with **Belzona® 4361** not exceeding an area of 12 sq.ft. (1.1 m²) per 450g unit. Brush the **Belzona® 4911** well into the surface using a stiff bristled brush. Conditioning and overcoating must be completed within the times shown below:

Ambient Temperature	Usable life after mixing	Minimum overcoating time	Maximum overcoating time*
59°F/15°C	55 mins	Application can commence as soon as it is possible to do so without disturbing the Conditioner	6 hours
68°F/20°C	45 mins		6 hours
77°F/25°C	32 mins		6 hours
86°F/30°C	20 mins		6 hours

* If the maximum overcoating time for the **Belzona® 4911** is exceeded, then the cured surface should be abraded and fresh **Belzona® 4911** applied.

2. COMBINING THE REACTIVE COMPONENTS

Add the entire contents of the **Belzona® 4361** Solidifier component to the Base unit.

Mix thoroughly until a completely homogeneous liquid, free of any streaks, is achieved.

NOTES:

1. WORKING LIFE

From the commencement of mixing, **Belzona® 4361** must be used within the following times.

Temperature	59°F(15°C)	68°F(20°C)	86°F(30°C)	104°F(40°C)
Use all material within	60 min.	30 min.	20 min.	15 min.

2. MIXING RATIO

For mixing small quantities of **Belzona® 4361**, use:
3 parts Base to 1 part Solidifier by weight, or
2.8 parts Base to 1 part Solidifier by volume

3. VOLUME CAPACITY OF MIXED **BELZONA® 4361**

76 cu.in. (1240 cm³) per 1.5 kg unit.

3. APPLYING **BELZONA® 4361**

FOR BEST RESULTS

Do not apply when:-

- The temperature is below 59°F (15°C) or the relative humidity is above 80%.
- Rain, snow, fog or mist is present.
- There is moisture on the metal surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

Belzona® 4361 is best applied when the temperature of the material, substrate and environment is anywhere between 59°F (15°C) and 86°F (30°C). Below 59°F (15°C), the material will be too stiff for easy mixing and application. Above 86°F (30°C), the material may be somewhat fluid and will have a short usable life.

Reference must also be made to the cure times. Below 59°F (15°C), the rate of cure is drastically reduced and some external heat source must be used to affect full cure.

COVERAGE RATES

Recommended number of coats	2
Target thickness 1 st coat	10 mils (250 microns)
Target thickness 2 nd coat	10 mils (250 microns)
Minimum total DFT	16 mils (400 microns)
Maximum total DFT	24 mils (600 microns)
Theoretical coverage rate 1 st coat	53.4 sq.ft/1.5kg unit (4.96 m ² /1.5kg unit)
Theoretical coverage rate 2 nd coat	53.4 sq.ft/1.5kg unit (4.96 m ² /1.5kg unit)
Theoretical coverage rate to achieve minimum recommended system thickness	33.4 sq.ft/1.5kg unit (3.1 m ² /1.5kg unit)

PRACTICAL COVERAGE RATES

Appropriate loss factors must be applied to the above coverage rates. In practice, many factors influence the actual coverage rate achieved. On rough surfaces such as pitted steel the practical coverage rate will be reduced. Application at low temperatures will also reduce practical coverage rates further.

- Apply the mixed material using a short bristled brush or squeegee to the prepared surface.
- Apply a further coat of **Belzona® 4361** as in (a). Apply the second layer as soon as it is possible to do so without disturbing the first layer. The maximum overcoat time is 24 hours when working at temperatures between 59°F (15°C) and 86°F (30°C).
- If the maximum overcoating time for the **Belzona® 4361** is exceeded, then the cured surface should be abraded and fresh **Belzona® 4361** applied.

NOTES:

1. COLOR

Belzona® 4361 is available in black and red to facilitate application and to prevent misses. These colors are for identification only and there may be some variation between batches. In service the color of the applied product may change.

2. CLEANING

Mixing and application tools should be cleaned immediately after use with **Belzona® 9111** (Cleaner/Degreaser) or any other effective solvent e.g. MEK. Brushes, injection guns, spray equipment and other application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 4361** to solidify as below before subjecting it to the conditions indicated:

	Light pedestrian traffic	Vehicular traffic	Full chemical resistance
59°F/15°C	7 hours	48 hours	14 days
68°F/20°C	5 hours	36 hours	7 days
77°F/25°C	4 hours	24 hours	6 days
86°F/30°C	3 hours	20 hours	5 days

NOTE: Below 59°F (15°C) solidification times will be significantly extended and the resultant chemical resistance capability of the **Belzona® 4361** may be reduced.

5. STORAGE

For optimal shelf life, do not store above 25°C.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2017 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

**BELZONA**
Repair • Protect • Improve