

# PRODUCT SPECIFICATION SHEET

## BELZONA 1161

FN 10185



### GENERAL INFORMATION

**Product Description:**

Two component, surface tolerant, paste grade system for repairing and rebuilding machinery and equipment. Based on a silicon steel alloy blended with high molecular weight reactive polymers and oligomers. Ideal for use as a high strength structural bonding adhesive or for the creation of irregular load bearing shims.

**Application Areas:**

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to damp and oil contaminated surfaces. In addition, the material can be applied underwater.

### APPLICATION INFORMATION

**Application Methods**

Plastic applicator and spatula

**Application Temperature**

Application should ideally occur in the following ambient temperature range: 41°F/5°C to 104°F/40°C

**Volume Capacity**

The volume capacity of mixed material is 428 cm<sup>3</sup> (26.1 in<sup>3</sup>)/kg.

**Cure Time**

Cure times will vary depending on the ambient conditions and application thickness. Consult the Belzona IFU for specific details.

**Working Life**

The working life will vary according to temperature. At 68°F/20°C, the usable life of mixed material will typically be 16 minutes, consult the Belzona IFU for specific details.

**Base Component**

Colour: Dark Grey  
Form: Paste  
Density: 2.80 g/cm<sup>3</sup>  
Gel Strength (HF paddle): >150 g/cm

**Solidifier Component**

Colour: Light Grey  
Form: Paste  
Density: 1.40 g/cm<sup>3</sup>  
Gel Strength (QV paddle): 90 g/cm

**Mixed Properties**

Mixing Ratio by Weight (Base : Solidifier) 4 : 1  
Mixing Ratio by Volume (Base : Solidifier) 2 : 1  
Colour: Grey  
Mixed Form: Paste  
Mixed Density: 2.34 g/cm<sup>3</sup>  
Slump Resistance: >0.5 in / >12.7 mm  
VOC (ASTM D2369): 0.10 % / 2.39 g/L

*The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.*

# PRODUCT SPECIFICATION SHEET

## BELZONA 1161

### FN 10185



#### ADHESION

##### Cleavage Adhesion

The Cleavage Adhesion on mild steel substrates, as determined in accordance with ASTM D1062, following a 7 day cure at 68°F/20°C, will typically be:

|   | Cleavage Adhesion   | Failure Mode |
|---|---------------------|--------------|
| Grit Blasted (SSPC-SP10) (ISO 8501-1 Sa2.5) | 1810 pli / 317 N/mm | Cohesive     |
| Ground (SSPC-SP11) (ISO 8501-1 St3)         | 1751 pli / 306 N/mm | Cohesive     |

##### Pull Off Adhesion

The PosiTest Dolly Pull Off Strength on 10mm thick mild steel, as determined in accordance with ASTM D4541 and ISO 4624, following a 7 day cure at 68°F/20°C, will typically be:

| Substrate       | Grit Blasted (SSPC-SP10) (ISO 8501-1 Sa2.5) | Ground (SSPC-SP11) (ISO 8501-1 St3) |
|-----------------|---|-------------------------------------|
| Clean & Dry     | 5036 psi / 34.7 MPa                         | 5183 psi / 35.8 MPa                 |
| Transformer Oil | 3603 psi / 24.9 MPa                         | 4459 psi / 30.8 MPa                 |
| Wet             | 2035 psi / 14.0 MPa                         | 3426 psi / 26.6 MPa                 |
| Underwater      | 1873 psi / 12.9 MPa                         | 2588 psi / 17.9 MPa                 |

##### Tensile Shear Adhesion

The Tensile Shear Adhesion on mild steel substrates, as determined in accordance with ASTM D1002, following a 7 day cure at 68°F/20°C, will typically be:

| Substrate       | Grit Blasted (SSPC-SP10) (ISO 8501-1 Sa2.5) | Ground (SSPC-SP11) (ISO 8501-1 St3) |
|-----------------|---|-------------------------------------|
| Clean & Dry     | 3007 psi / 20.7 MPa                         | 2130 psi / 14.7 MPa                 |
| Transformer Oil | 2735 psi / 18.9 MPa                         | 2256 psi / 15.6 MPa                 |
| Wet             | 2284 psi / 15.8 MPa                         | 1869 psi / 12.9 MPa                 |
| Underwater      | 1982 psi / 13.7 MPa                         | 1574 psi / 10.9 MPa                 |

The Tensile Shear Adhesion on various metal substrates, as determined in accordance with ASTM D1002, following a 7 day cure at 68°F/20°C, will typically be:

| Substrate       | Grit Blasted (SSPC-SP10) (ISO 8501-1 Sa2.5) | Ground (SSPC-SP11) (ISO 8501-1 St3) |
|-----------------|---|-------------------------------------|
| Aluminum        | 1391 psi / 9.6 MPa                          | 1340 psi / 9.2 MPa                  |
| Brass           | 2122 psi / 14.6 MPa                         | 1849 psi / 12.8 MPa                 |
| Copper          | 1862 psi / 12.8 MPa                         | 1544 psi / 10.6 MPa                 |
| Stainless Steel | 2187 psi / 15.1 MPa                         | 1685 psi / 11.6 MPa                 |

#### ABRASION

##### Taber

When determined in accordance with ASTM D4060 using a 1kg load, the sliding Taber abrasion resistance will typically be:

|   |                           |
|---|---------------------------|
| <b>Dry</b> (CS17 Wheels)<br>43 mm <sup>3</sup> loss per 1000 cycles | (7 day cure at 68°F/20°C) |
| <b>Wet</b> (H10 Wheels)<br>712 mm <sup>3</sup> loss per 1000 cycles | (7 day cure at 68°F/20°C) |

#### COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

|   |   |
|---|---|
| <b>Compressive Strength (Maximum)</b><br>9949 psi / 68.6 MPa<br>12007 psi / 82.8 MPa<br>15343 psi / 105.8 MPa   | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |
| <b>Compressive Strength (Yield)</b><br>7690 psi / 53.0 MPa<br>9459 psi / 65.2 MPa<br>10745 psi / 74.1 MPa   | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |
| <b>Compressive Modulus</b><br>1.60 x 10 <sup>5</sup> psi / 1104 MPa<br>1.79 x 10 <sup>5</sup> psi / 1237 MPa<br>1.87 x 10 <sup>5</sup> psi / 1287 MPa | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |

#### ELONGATION & TENSILE PROPERTIES

When determined in accordance with ASTM D638, typical values will be:

|   |   |
|---|---|
| <b>Tensile Strength (Maximum)</b><br>3788 psi / 26.1 MPa<br>3719 psi / 25.7 MPa<br>4743 psi / 32.7 MPa  | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |
| <b>Tensile Strength (Yield)</b><br>1572 psi / 10.8 MPa<br>2841 psi / 19.6 MPa<br>3074 psi / 21.2 MPa  | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |
| <b>Elongation</b><br>0.57 %<br>0.49 %<br>0.52 %   | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |
| <b>Young's Modulus</b><br>7.63 x 10 <sup>5</sup> psi / 5263 MPa<br>8.33 x 10 <sup>5</sup> psi / 5741 MPa<br>8.44 x 10 <sup>5</sup> psi / 5823 MPa | (24 hour cure at 68°F/20°C)<br>(7 day cure at 68°F/20°C)<br>(7 day post cure at 194°F/90°C) |

# PRODUCT SPECIFICATION SHEET

## BELZONA 1161

### FN 10185



#### FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

##### Flexural Strength (Maximum)

8793 psi / 60.6 MPa (24 hour cure at 68°F/20°C)  
 9361 psi / 64.6 MPa (7 day cure at 68°F/20°C)  
 10785 psi / 76.4 MPa (7 day post cure at 194°F/90°C)

##### Flexural Strength (Yield)

4434 psi / 30.6 MPa (24 hour cure at 68°F/20°C)  
 5571 psi / 38.4 MPa (7 day cure at 68°F/20°C)  
 6554 psi / 45.2 MPa (7 day post cure at 194°F/90°C)

##### Flexural Modulus

7.28 x 10<sup>5</sup> psi / 5019 MPa (24 hour cure at 68°F/20°C)  
 8.45 x 10<sup>5</sup> psi / 5826 MPa (7 day cure at 68°F/20°C)  
 8.11 x 10<sup>5</sup> psi / 5594 MPa (7 day post cure at 194°F/90°C)

#### HARDNESS

The Shore D and Barcol hardness, when determined in accordance with ASTM D2240 and ASTM D2583 (Model No.935) respectively, will typically be:

|                               | Shore D | Barcol |
|-------------------------------|---------|--------|
| 24 hour cure at 68°F/20°C     | 83      | 81     |
| 7 day cure at 68°F/20°C       | 84      | 83     |
| 7 day post cure at 194°F/90°C | 87      | 86     |

#### HEAT RESISTANCE

##### Heat Distortion (HDT)

The HDT when determined in accordance with ASTM D648, will typically be:

| Cure                          | HDT        |
|-------------------------------|------------|
| 24hrs at 68°F/20°C            | 104°F/40°C |
| 7 days at 68°F/20°C           | 117°F/47°C |
| 7 day post cure at 194°F/90°C | 154°F/68°C |

##### Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO 11357 is typically 401°F/208°C.

For many applications, the product is suitable down to -40°F/-40°C.

#### IMPACT RESISTANCE

##### Izod Pendulum

Izod impact strength, when determined in accordance with ASTM D256, will typically be:

Notched: 3.99 KJ/m<sup>2</sup> (7 day cure at 68°F/20°C)  
 6.34 KJ/m<sup>2</sup> (7 day post cure at 194°F/90°C)  
 Un-notched: 4.98 KJ/m<sup>2</sup> (7 day cure at 68°F/20°C)  
 7.70 KJ/m<sup>2</sup> (7 day post cure at 194°F/90°C)

#### SHELF LIFE

Separate base and solidifier components shall have a shelf life of 3 years from date of manufacture when stored in their original unopened containers between 32°F (0°C) and 86°F (30°C).

# PRODUCT SPECIFICATION SHEET

## BELZONA 1161

FN 10185



### WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

### AVAILABILITY AND COST

**Belzona 1161** will be available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

### HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

### MANUFACTURER

Belzona Polymerics Ltd.  
Claro Road, Harrogate,  
HG1 4DS, UK

Belzona Inc.  
2000N.W. 88<sup>th</sup> Court,  
Miami, Florida, USA, 33172

### TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2016 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are  
manufactured under an  
ISO 9001 Registered  
Quality Management System*

