

PRODUCT SPECIFICATION SHEET

BELZONA 2111

FN10179



GENERAL INFORMATION

Product Description:

Two component, durable and abrasion resistant, high build elastomeric system designed for repairing, resurfacing and rebuilding.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for the following applications where significant thickness and durability are required:

- Rubber linings / sheeting
- Conveyor belts; flight build up
- Conveyor belts; clip joint protection
- Outer sheath of trailing mining cables
- Chutes, screens and wear plates
- Storage hoppers
- Pumps and impellers

APPLICATION INFORMATION

Application Methods

Applicator
Spatula

Gel Time & Working Life

The gel time and working life will vary according to temperature. At 68°F/20°C the gel time and usable life of mixed material will typically be 4 and 12 minutes respectively. Consult the Belzona IFU for specific details.

Cure Time

Cure times will vary depending on ambient conditions; consult the Belzona IFU for specific details.

Volume Capacity

The volume capacity of mixed material will be
54 cu.in. (885cm³)/kg
27.0 cu.in. (442cm³) per 500g unit.

Base Component

Appearance Pale straw colored viscous liquid
Density 1.1 – 1.2 g/cm³
Viscosity 190-330 P at 77°F/25°C

Solidifier Component

Appearance Thin black liquid
Density 1.07 g/cm³
Viscosity 12.5 P at 77°F/25°C

Mixed Properties

Appearance Black paste
Density 1.13 g/cm³
Slump Resistance 0.5 inch / 12.7 mm
VOC content (ASTM D2369/EPA ref 24) 0.16%/1.85 g/L
Mixing Ratio by Weight (Base : Solidifier) 3.4 : 1
Mixing Ratio by Volume (Base : Solidifier) 3.2 : 1

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 2111

FN10179



ABRASION

Taber

When determined in accordance with ASTM D4060 using H18 wheels and 1kg load, the sliding Taber abrasion resistance will be:

Dry

41 mm³ loss per 1000 cycles (7 day cure at 68°F/20°C)

Wet

16 mm³ loss per 1000 cycles (7 day cure at 68°F/20°C)

ADHESION

90° Peel Adhesion

When tested in accordance with ASTM D429 (modified), typical adhesion values achieved when the material is used in conjunction with the designated surface and recommended surface conditioner will be:

Substrate	Peak Adhesion	Failure Mode
Grit Blasted Mild Steel	172 pli 3065 kg/m	Tape Failure

180° Peel Adhesion

When tested in accordance with ASTM D413, typical adhesion values achieved when the material is used in conjunction with the designated surface and recommended surface conditioner will be:

Substrate	Peak Adhesion	Average Peel Adhesion	Failure Mode
EPDM (Shore A: 75)	24 pli 425 kg/m	6 pli 115 kg/m	Cohesive in Substrate
Nitrile (Shore A: 77)	39 pli 690 kg/m	20 pli 360 kg/m	Cohesive in Substrate
Neoprene (Shore A: 83)	20 pli 365 kg/m	13 pli 240 kg/m	Cohesive in Substrate
Natural Rubber (Shore A: 51)	22 pli 385 kg/m	7 pli 120 kg/m	Cohesive in Substrate
Commercial Rubber (Natural/SBR) (Shore A: 72)	24 pli 435 kg/m	13 pli 230 kg/m	Cohesive in Substrate
Insertion Rubber (commercial with textile reinforcement) (Shore A: 70)	20 pli 360 kg/m	6 pli 115 kg/m	Cohesive in Substrate

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate excellent resistance to a range of chemicals including; dilute inorganic acids and alkalis.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

COMPRESSION RESISTANCE

When tested in accordance with BS 903 part A6, the compression set following a 30 minute recovery period will typically be 22%.

ELECTRICAL PROPERTIES

Dielectric Strength

When tested in accordance with ASTM D149 the dielectric strength will typically be 7.1 kV/mm (177 V/mil) when tested at 500 V/s

Dielectric Constant

When tested in accordance with ASTM D150 the dielectric constant will typically be 5.02 when tested at 1.0 V and 100 Hz

Dissipation Factor

When tested in accordance with ASTM D150 the dissipation factor will typically be 0.021 when tested at 1.0 V and 100 Hz

Surface Resistivity

When tested in accordance with ASTM D257 the surface resistivity will typically be 7.66 x 10¹² Ω when tested at 500 V DC

Volume Resistivity

When tested in accordance with ASTM D257 the volume resistivity will typically be 2.30 x 10¹² Ωcm when tested at 500 V DC

ELONGATION & TENSILE PROPERTIES

When tested in accordance with ASTM D412 (Die C) the tensile properties will typically be:

	24 hours at 68°F/20°C	7 days at 68°F/20°C
Tensile Strength	1970 psi 13.6 MPa	2355 psi 16.2 MPa
Tensile Modulus	180 psi 1.3 MPa	335 psi 2.3 MPa
Elongation	450-550 %	350-450 %

PRODUCT SPECIFICATION SHEET

BELZONA 2111

FN10179



HARDNESS

Shore A Hardness:

Tested in accordance with ASTM D2240 typical value will be;

91 (24 hour cure at 68°F/20°C)
93 (7 day cure at 68°F/20°C)

TEAR STRENGTH

Tear Strength

When tested in accordance with ASTM D624 will typically be:

370 pli / 6600 kg/m (24 hour and 7 day cure at 68°F/20°C)

HEAT RESISTANCE

Dry

For many typical applications the product will be suitable for operation in dry conditions in the temperature range -40°F to 194°F (-40°C to 90°C).

Wet

For wet or immersed conditions the maximum service temperature is 104°F (40°C).

SHELF LIFE

Separate base and solidifier components shall have a shelf life of 3 years from date of manufacture when stored in their original unopened containers between 41°F (5°C) and 86°F (30°C).

PRODUCT SPECIFICATION SHEET

BELZONA 2111

FN10179



WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 2111 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000 N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2018 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

