

PRODUCT SPECIFICATION SHEET

BELZONA 5721

FN10204



GENERAL INFORMATION

Product Description:

A high performance, two component, solvent free coating system for the protection of leading edges on wind turbine blades. For use in repair situations or Original Equipment Manufacture (OEM). **Belzona 5721** offers high erosion resistance, is optimised for ease of application and a rapid return to service.

APPLICATION INFORMATION

Application Methods

Brush

Application Temperature

Application should occur in the following ambient temperature range: 5°C/41°F to 40°C/104°F.

Coverage Rate

Belzona 5721 can be applied as a one coat or two coat system at a target thickness of 500 microns (20 mil) per coat.

Applied at a thickness of 500 microns (20 mil), the theoretical coverage rate will be 1.3 m² (14.0 sq.ft)/kg.

Cure Time

The cure time is dependent on ambient conditions. Allow to cure for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

Base Component

Appearance	Thixotropic liquid
Colour	White or Light Grey
Density	1.72 - 1.74 g/cm ³

Solidifier Component

Appearance	Liquid
Colour	Clear, colourless
Density	1.11 - 1.15 g/cm ³

Mixed Properties

Appearance:	Thixotropic liquid
Colour:	White or Light Grey (RAL 7035)
Density	1.51 g/cm ³
Sag resistance (BS 5350-B9):	750 µm / 30 mils
60° Specular Gloss (ASTM D2457):	88 Gloss Units
VOC content (ASTM D2369 / EPA ref. 24):	0.13% / 1.89 g/L

Mix Ratio

Mixing Ratio by Weight (Base : Solidifier)	2.66 : 1
Mixing Ratio by Volume (Base : Solidifier)	1.75 : 1

Overcoat Window

Between an ambient temperature range of 5°C/41°F to 40°C/104°F, the minimum overcoat time will be 30 minutes. The maximum overcoat time will be 24 hours. Consult the Belzona IFU for specific details.

Working Life

The working life will vary depending on ambient conditions. At 20°C/68°F and 50% relative humidity, the usable life of mixed material will typically be 40 minutes. Consult the Belzona IFU for specific details.

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 5721

FN10204



ADHESION	
Pull Off Adhesion The PosiTest Dolly Pull Off Strength on GRP composite, as determined in accordance with ASTM D4541 and ISO 4624, will typically be:	
10.5 MPa / 1520 psi*	20°C/68°F cure & test
*Cohesive failure of GRP composite	
The PosiTest Dolly Pull Off Strength on 10mm thick grit blasted mild steel, as determined in accordance with ASTM D4541 and ISO 4624, will typically be:	
36.8 MPa / 5340 psi	20°C/68°F cure & test
Tensile Shear Adhesion The tensile shear adhesion on grit blasted mild steel, as determined in accordance with ASTM D1002, will typically be:	
25.2 MPa / 3650 psi	20°C/68°F cure & test
Tensile Shear Adhesion (Immersion) The Tensile Shear Adhesion on mild steel, as determined in accordance with ASTM D1002, tested at 20°C after 1000 hours immersion in tap water at 40°C/104°F, will typically be:	
19.2 MPa / 2780 psi	20°C/68°F test
Cleavage Adhesion The cleavage adhesion on grit blasted mild steel, as determined in accordance with ASTM D1062, will typically be:	
314 N/mm / 1800 pli	20°C/68°F cure & test

COMPRESSIVE PROPERTIES	
When determined in accordance with ASTM D695, typical values will be:	
Compressive Yield Strength 42.4 MPa / 6140 psi	
	20°C/68°F cure & test
Compressive Modulus 1050 MPa / 1.52 x 10 ⁵ psi	
	20°C/68°F cure & test

CORROSION PROTECTION	
Salt Spray When tested in accordance with ASTM B117, Belzona 5721 will show no signs of failure after 13,000 hours continuous exposure.	
Water Immersion When tested in accordance with ISO 2812-2, Belzona 5721 will show no signs of failure after 1000 hours continuous immersion at 40°C/104°F in deionised water.	

EROSION RESISTANCE		
Taber Dry sliding abrasion resistance, when determined in accordance with ASTM D4060 using CS17 wheels, will typically result in:		
16 mm ³ loss per 1000 cycles	20°C/68°F cure & test	
Grit Impact Direct impact of 2kg G34 chilled iron grit at 80 psi and 90° angle, will typically result in volume loss of:		
15 mm ³	20°C/68°F cure & test	
Solid Particle Impingement When independently tested at a coating thickness of 500 microns, in accordance with ASTM G76, using 50g dry silica sand jet erosion, at a distance of 20mm from the surface, at an impingement angle of 90° and at an erodent velocity of 70 m/s, the volume loss will typically be:		
8.8 mm ³	20°C/68°F cure & test	
Rain Erosion Testing (RET) When independently tested at a coating thickness of 500 microns, in accordance with ASTM G73 at a tip velocity of 160 m/s, the coating will show no significant damage following 3 hours of continuous testing.		
When independently tested in accordance with ASTM G73 and DNVGL-RP-0171 with a flow rate of 65 L/hr and mean droplet size of 2.46mm, the breakthrough to substrate time was:		
	Tip Velocity	
Product Thickness	125 m/s	150 m/s
500 microns (1 coat)	13 hrs	2 hrs
1000 microns (2 coats)	21 hrs	3.5 hrs
Cavitation Resistance When tested to a modified version of ASTM G32 using stationary specimens at 20 kHz frequency and 50 microns amplitude, will typically result in:		
58 mm ³ loss in 8 hours	20°C/68°F cure & test	

FLEXURAL PROPERTIES	
When determined in accordance with ASTM D790, typical values will be:	
Flexural Strength 59.2 MPa / 8580 psi	20°C/68°F cure & test
Flexural Modulus 3330 MPa / 4.83 x 10 ⁵ psi	20°C/68°F cure & test

PRODUCT SPECIFICATION SHEET

BELZONA 5721

FN10204



HARDNESS

Shore D

The Shore D hardness of the material tested to ASTM D2240 is typically:

81 20°C/68°F cure & test

Barcol (Model 935)

The Barcol hardness of the material tested to ASTM D2583 is typically:

78 20°C/68°F cure & test

König Pendulum

When tested to ISO 1522 the König damping time of the coating will typically be:

161 seconds 20°C/68°F cure & test

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

When determined in accordance with ASTM D648, the HDT will typically be:

49°C / 120°F 20°C/68°F cure

IMPACT STRENGTH

Izod Impact

When tested in accordance with ASTM D256, the reverse notched impact strength will typically be:

14.9 kJ/m² 20°C/68°F cure & test

Falling Weight

The direct falling weight impact resistance when determined in accordance with ASTM D2794 will typically be

0.91 kg.m / 78.7 in.lbs 20°C/68°F cure & test

UV RESISTANCE

Artificial Weathering (Xenon Arc)

When tested in accordance with ISO 4892-2 (Xenon Arc), **Belzona 5721** will show no chalking or colour change following >4000 hours exposure.

SHELF LIFE

Separate base and solidifier components shall have a shelf life of 3 years from date of manufacture when stored in their original unopened containers between 5°C (41°F) and 30°C (86°F).

PRODUCT SPECIFICATION SHEET

BELZONA 5721

FN10204



WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 5721 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

MANUFACTURER / SUPPLIER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
14300 N.W. 60th Ave.
Miami Lakes, FL, 33014, USA

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Safety Data Sheets.

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2021 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

