

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### GENERAL INFORMATION

#### Product Description:

A novel, two-component, polymeric, solvent-free system, that expands to produce a lightweight, closed-cell foam to provide corrosion protection combined with thermal and subzero cool-to-touch insulation properties.

Hand or spray applied thermal insulation system, suitable for dry heat up to 150°C/302°F and for wet conditions up to 120°C/248°F.

Exhibits excellent corrosion resistance at ambient, elevated and sub-zero temperatures.

#### Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to metal pipework, ducting and other industrial equipment to provide:

- Worksite personal protection and safety against contact-burn injuries
- Corrosion (CUI) protection
- Thermal insulation
- Condensation prevention
- Anti-icing

### APPLICATION INFORMATION

#### Application Methods

Brush  
Cartridge Spray  
Heated Plural Airless Spray

#### Application Temperature

For best results, application should occur in the following ambient temperature range: 5°C/41°F to 40°C/104°F. Consult the Belzona IFU for specific details.

#### Coverage Rate

When applied at 1000 microns wet film thickness to give 3000 microns dry film thickness (due to foaming action), the theoretical coverage rate will be 1.0 m<sup>2</sup> (10.8 sq. ft.) per litre.

#### Cure Time

Cure times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.

#### Base Component

Appearance: Thixotropic liquid  
Colour: White  
Density: 1.16 g/cm<sup>3</sup>

#### Solidifier Component

Appearance: Thixotropic liquid  
Colour: Orange  
Density: 1.01 g/cm<sup>3</sup>

#### Mixed Properties

Appearance: Thixotropic liquid  
Colour: Orange  
Applied density: 1.11 g/cm<sup>3</sup>  
Cured density: 0.35 - 0.40 g/cm<sup>3</sup>  
Sag resistance (BS 5350-B9): 1000 µm / 40 mils  
VOC content (ASTM D2369 / EPA ref. 24): 0.20% / 2.28 g/L

#### Mix Ratio

Mix ratio by weight (Base : Solidifier) 2.3 : 1  
Mix ratio by volume (Base: Solidifier) 2 : 1

#### Overcoat Window

Minimum overcoat times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.  
The maximum overcoat time will typically be 24 hours.

#### Working Life

The working life will vary according to the temperature. At 20°C/68°F, the usable life of mixed material will typically be 20 minutes. Consult the Belzona IFU for specific details.

*The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.*

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### ABRASION

#### Taber

Dry sliding abrasion resistance, when determined in accordance with ASTM D4060 using CS17 wheels, will typically result in:

777 mm<sup>3</sup> loss per 1000 cycles (20°C/68°F cure & test)

### ADHESION

#### Cleavage Adhesion

The Cleavage Adhesion on mild steel, as determined in accordance with ASTM D1062, will typically be:

Grit Blasted (ISO 8501-1 Sa 2.5)	Cleavage Adhesion
20°C/68°F cure & test	52 N/mm / 300 pli*
120°C/248°F cure & 20°C/68°F test	76 N/mm / 435 pli*

#### Pull Off Adhesion

The PosiTect Dolly Pull Off Strength on 10mm thick substrates, as determined in accordance with ASTM D4541 and ISO 4624, will typically be:

Mild Steel Grit Blasted (ISO 8501-1 Sa 2.5)	Pull Off Adhesion
20°C/68°F cure & test	4.5 MPa / 650 psi*
150°C/302°F cure & 20°C/68°F test	3.7 MPa / 530 psi*

Mild Steel Ground (SSPC-SP11 ≥25 microns)	Pull Off Adhesion
20°C/68°F cure & test	4.3 MPa / 620 psi*
120°C/248°F cure & 20°C/68°F test	4.7 MPa / 680 psi*

Mild Steel Grit Blasted (ISO 8501-1 Sa 2.5)	Pull Off Adhesion After Immersion in Deionised Water At 40°C/104°F **
20°C/68°F cure & test	3.0 MPa / 440 psi* (3000 hours immersion)
150°C/302°F cure & 20°C/68°F test	3.0 MPa / 440 psi* (2000 hours immersion)

Stainless Steel Grit Blasted (ISO 8501-1 Sa 2.5)	Pull Off Adhesion
20°C/68°F cure & test	4.7 MPa / 680 psi*
150°C/302°F cure & 20°C/68°F test	3.9 MPa / 570 psi*

\* Cohesive failure of Belzona 5871

\*\* Tested on 3mm thick mild steel substrates

### ADHESION

#### Tensile Shear Adhesion

The Tensile Shear Adhesion on mild steel, as determined in accordance with ASTM D1002, will typically be:

Grit Blasted ISO 8501-1 Sa 2.5	Tensile Shear Adhesion
20°C/68°F cure & test	8.6 MPa / 1250 psi*
60°C/140°F cure & 20°C/68°F test	10.9 MPa / 1580 psi*
90°C/194°F & 20°C/68°F test	11.7 MPa / 1700 psi*
120°C/248°F cure & 20°C/68°F test	11.8 MPa / 1710 psi*
150°C/302°F cure & 20°C/68°F test	9.9 MPa / 1430 psi*
60°C/140°F cure & test	7.3 MPa / 1060 psi*
90°C/194°F cure & test	7.4 MPa / 1070 psi*
120°C/248°F cure & test	4.3 MPa / 630 psi*
150°C/302°F cure & test	2.3 MPa / 340 psi*

Ground SSPC-SP11 ≥ 25 microns	Tensile Shear Adhesion
20°C/68°F cure & test	11.3 MPa / 1640 psi*
120°C/248°F cure & 20°C/68°F test	10.7 MPa / 1550 psi*
120°C/248°F cure & test	6.8 MPa / 990 psi*

#### Tensile Shear Adhesion (Immersion)

The Tensile Shear Adhesion on mild steel, as determined in accordance with ASTM D1002, tested at 20°C/68°F after 1000 hours immersion in water at 40°C/104°F, will typically be:

Grit Blasted ISO 8501-1 Sa 2.5	Tensile Shear Adhesion After Immersion in Water At 40°C/104°F
20°C/68°F cure & test	7.6 MPa / 1100 psi*
120°C/248°F cure & 20°C/68°F test	7.3 MPa / 1060 psi*

  

Ground SSPC-SP11 ≥ 25 microns	Tensile Shear Adhesion After Immersion in Water At 40°C/104°F
20°C/68°F cure & test	5.9 MPa / 860 psi*
120°C/248°F & 20°C/68°F test	4.6 MPa / 660 psi*

\* Cohesive failure of Belzona 5871

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### COMPRESSIVE PROPERTIES

When determined in accordance with ASTM D695, typical values will be:

	Compressive Strength	Limit of Elasticity	Compressive Modulus
20°C/68°F cure & test	9.4 MPa 1360 psi	6.8 MPa 980 psi	240 MPa 3.40 x 10 <sup>4</sup> psi
60°C/140°F cure & 20°C/68°F test	11.5 MPa 1670 psi	8.4 MPa 1210 psi	250 MPa 3.60 x 10 <sup>4</sup> psi
90°C/194°F cure & 20°C/68°F test	12.2 MPa 1770 psi	8.1 MPa 1170 psi	270 MPa 3.90 x 10 <sup>4</sup> psi
120°C/248°F cure & 20°C/68°F test	13.0 MPa 1880 psi	7.9 MPa 1140 psi	260 MPa 3.80 x 10 <sup>4</sup> psi
150°C/302°F cure & 20°C/68°F test	11.7 MPa 1700 psi	7.9 MPa 1150 psi	270 MPa 3.90 x 10 <sup>4</sup> psi
60°C/140°F cure & test	7.4 MPa 1070 psi	6.3 MPa 910 psi	250 MPa 3.60 x 10 <sup>4</sup> psi
90°C/194°F cure & test	7.0 MPa 1020 psi	4.9 MPa 710 psi	210 MPa 3.00 x 10 <sup>4</sup> psi

### CORROSION PROTECTION

#### Corrosion Under Insulation (CUI)

**Belzona 5871** when applied as a single or multi-layer system will show no signs of failure on grit blasted or ground mild steel after 1000 hours simulated CUI, cycled between 60°C/140°F and 120°C/248°F, with alternating, hourly dry and wet (constant deluge of water at 5 litres per minute\*) periods.

\* Equates to 300m<sup>3</sup> total water exposure over 1000 hours simulated CUI.

**Belzona 5871** when applied as a multi-layer system will show no signs of failure on grit blasted or ground mild steel after 1000 hours simulated CUI, cycled between 120°C/248°F and 10°C/50°F, with alternating, wet (constant deluge of water at 5 litres per minute) and dry periods\*\*.

#### \*\* Cycling regime:

- 4 days at 120°C/248°F (with alternating 4 hours wet exposure and 4 hours dry exposure)
- 3 days at 10°C/50°F (dry exposure only)

### CORROSION PROTECTION

#### Electrochemical Impedance Spectroscopy (EIS)

The EIS result ( $\log_{10}|Z|_{0.1\text{Hz}}$ ) on **Belzona 5871** (at 5.8 mm cured thickness), as determined in accordance with ISO 16773, will typically be:

12.1  $\Omega\cdot\text{cm}^2$  (20°C/68°F cure & test)

#### Electrochemical Impedance Spectroscopy (EIS Immersion)

The EIS result ( $\log_{10}|Z|_{0.1\text{Hz}}$ ) as determined in accordance with ISO 16773, measured after 1000 hours immersion in 1% KCl, with the steel substrate cycled between 120°C/248°F for five days and 20°C/68°F for two days, will typically be:

12.1  $\Omega\cdot\text{cm}^2$  (20°C/68°F test)

#### Salt Spray

When tested in accordance with ASTM B117, **Belzona 5871** tested as a one-layer system (at 3.0 mm cured thickness), cured at 20°C/68°F and post cured at 120°C/248°F respectively, will show no signs of failure after 4500 hours continuous exposure.

#### Water Immersion

When tested in accordance with ISO 2812-2, continuous immersion at 40°C/104°F in deionised water, **Belzona 5871** tested as a one-layer system (at 3.0 mm cured thickness) will show no signs of failure after:

4500 hours (20°C/68°F cure)  
2000 hours (120°C/248°F cure)

When tested in accordance with NACE TM 0174 procedure B, **Belzona 5871** tested as a one-layer system (at 3.0 mm cured thickness), cured at 20°C/68°F, will exhibit no blistering or rusting (ASTM D714 rating 10; ASTM D610 rating 10) after 6 months immersion in deionised water at 40°C/104°F.

### ELONGATION & TENSILE PROPERTIES

When determined in accordance with ASTM D638, typical values will be:

	Elongation	Tensile Strength	Young's Modulus
20°C/68°F cure & test	0.49%	1.9 MPa 280 psi	370 MPa 5.30 x 10 <sup>4</sup> psi
120°C/248°F cure & 20°C/68°F test	0.56%	2.5 MPa 360 psi	400 MPa 5.80 x 10 <sup>4</sup> psi

### HARDNESS

The König Pendulum Hardness, when determined in accordance with ISO 1522, will typically be:

126 seconds (20°C/68°F cure & test)

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### HEAT RESISTANCE

#### Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO 11357 is typically 220°C (428°F).

For typical dry applications, **Belzona 5871** is suitable for use up to 150°C (302°F).

#### Glass Transition Temperature (T<sub>g</sub>)

The T<sub>g</sub> when determined in accordance with ISO 11357-2 respectively, following a 7-day cure period, will typically be:

Cure temperature	T <sub>g</sub>
20°C/68°F	61°C/142°F
60°C/140°F	98°C/208°F
90°C/194°F	116°C/240°F
120°C/248°F	116°C/240°F
150°C/302°F	116°C/240°F

### SUB-ZERO PROPERTIES

#### Pull Off Adhesion

When tested in accordance with ASTM D4541 and ISO 4624 on 10mm thick, grit blasted (ISO 8501-1 Sa 2.5) mild steel substrates, pull off adhesion will typically be:

4.1 MPa / 590 psi\* (20°C/68°F cure & -30°C/-22°F test)  
\* *Cohesive failure of Belzona 5871*

#### Tensile Shear Adhesion

When tested in accordance with ASTM D1002, on grit blasted (ISO 8501-1 Sa 2.5) mild steel, tensile shear adhesion will typically be:

8.7 MPa / 1270 psi\* (20°C/68°F cure & -10°C/14°F test)  
\* *Cohesive failure of Belzona 5871*

#### Low Temperature Limit

For typical applications, **Belzona 5871** is suitable for use down to -40°C (-40°F).

### IMPACT RESISTANCE

#### Izod Pendulum

Izod impact strength, when determined in accordance with ASTM D256, will typically be:

	Izod Impact Strength
Un-notched (20°C/68°F cure & test)	0.30 KJ/m <sup>2</sup>
Reversed notched (20°C/68°F cure & test)	0.38 KJ/m <sup>2</sup>

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### THERMAL PROPERTIES

#### Cool-To-Touch Surface

In accordance with the temperature limits and contact times detailed in ASTM C1055, **Belzona 5871** can be used to prevent contact-burn injuries by reducing the surface temperature of metallic substrates to below 60°C (140°F).

E.g. At 100°C/212°F substrate temperature, **Belzona 5871** applied at approximately 1500 microns wet film thickness, will reduce the surface temperature to 60°C/140°F.

Additionally, due to the reduced heat energy transfer of the system, **Belzona 5871** can offer a safe touch surface for ≥ 5 seconds at temperatures greater than 60°C/140°F.

Please refer to **Belzona 5871** IFU for thickness requirements.

#### Thermal Conductivity

When tested in accordance with EN 12667 and ASTM C177, the thermal conductivity will typical be:

Test Temperature	Thermal Conductivity (λ/ W/m.k)
-40°C/-40°F	0.0645
-20°C/-4°F	0.0675
0°C/32°F	0.0698
20°C/68°F	0.0723
60°C/140°F	0.0770
120°C/248°F	0.0844
150°C/302°F	0.0874

#### Thermal Cycling

When tested in accordance with ISO 19277, **Belzona 5871** applied onto steel substrates exhibited no cracking after:

20 cycles between 15°C/59°F and 150°C/302°F (20°C/68°F cure)  
50 cycles between -30°C/-22°F and 120°C/248°F (20°C/68°F cure)

### UV RESISTANCE

When tested in accordance with ISO 4892-2 (Xenon Arc), **Belzona 5871** overcoated with **Belzona 3211** will not show significant chalking or colour change after 8500 hours exposure.

### SHELF LIFE

Separate base and solidifier components shall have a shelf life of 2 years from date of manufacture when stored in their original unopened containers between 5°C (41°F) and 30°C (86°F).

# PRODUCT SPECIFICATION SHEET

## BELZONA 5871

FN10198



### WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

### AVAILABILITY AND COST

**Belzona 5871** is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

### SUPPLIER

Belzona Polymerics Ltd.  
Claro Road, Harrogate,  
HG1 4DS, UK

Belzona Inc.  
14300 N.W. 60th Ave.  
Miami Lakes, FL, 33014, USA

### HEALTH AND SAFETY

Prior to using this material, please consult the relevant Safety Data Sheets.

### TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2021 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are  
manufactured under an  
ISO 9001 Registered  
Quality Management System*

